






AT-4 WAXY RUST PROTECTION, 3004, 3033, 3034, 3035, 3036



Very efficient corrosion inhibitor for long-time protection of metal surfaces that are exposed to harsh weather conditions. Forms a solid, wax-like and flexible film that has an excellent UV protection. The dried film is heat stable up to approx. +200 °C. Displaces moisture. Excellent salt spray resistance, salt spray test according to ASTM B-117, 2-3 mils (50-75 microns), carbon steel (1010) 900-1500 h. Can be removed with hydrocarbon solvents or alkaline cleaning agents. Meets the following standards: MIL-PRF-16173 E (Grades 1 and 2), NATO 6850-66-132-5848 and 6850-66-132-6099 as well as NSN 8030-00-062-6950, 8030-00-231-2345, 8030-00-244-1300 and 8030-01-470-2601. Properties: coverage capacity form 7 to 8 m²/l @ 75 micron surface, dry film in 12-24 h, touch dry in 0.5-3 h, the carrier is petroleum distillate, shelf life in vessels 24 months @ 24 °C temp, non-volatile components 57-61 %, viscosity @ 23 °C 600-5000 cps (6 rpm) Spindle # 2, VOC 347-372 g/l, density 0.89-0.91 kg/l.

| Article number | Package size | Package | Batch/PCS | UN-code | EAN-code |
|----------------|--------------|--------------|-----------|---------|--|
| 3004 | 400/520 ml | aerosol | 12 | |  6 416631 030042 |
| 3033 | 5 l | tin canister | 1 | |  6 416631 030332 |
| 3034 | 10 l | tin canister | 1 | |  6 416631 030349 |
| 3035 | 25 l | tin canister | 1 | |  6 416631 030356 |
| 3036 | 200 l | barrel | 1 | |  6 416631 030363 |